## **AMENDMENTS TO THE CLAIMS**

This listing of claims will replace all prior versions and listings of claims in the application:

## **LISTING OF CLAIMS:**

- 1. (currently amended): A polyester resin composition comprising an inorganic filler, polyetherimide, and a polymer containing polyethylene naphthalate in a constituent unit thereof, wherein the inorganic filler is a swellable lamellar silicate <u>organized by an organizing agent</u>, wherein the organizing agent is an organo-onium ion selected from the group consisting of ammonium ion, phosphonium ion and sulfonium ion.
- **2. (original):** The polyester resin composition of claim 1, wherein a polymerization ratio of polyethylene naphthalate constituting the polymer is 1 to 100% by mol.
- **3. (original):** The polyester resin composition of claim 1, wherein the polymer is a copolymer containing polyethylene terephthalate and polyethylene naphthalate as copolymerized components.
- **4. (original):** The polyester resin composition of claim 2, wherein the polymer is a copolymer containing polyethylene terephthalate and polyethylene naphthalate as copolymerized components.

U.S. APPLN. NO. 10/642,577

AMENDMENT UNDER 37 C.F.R. § 1.116 U.S. APPLN. NO. 10/642,577

- **5.** (**previously presented**): The polyester resin composition of claim 1, wherein the content of the polyetherimide is 50 to 200 parts by mass with respect to 100 parts by mass of the inorganic filler.
- **6. (previously presented):** The polyester resin composition of claim 2, wherein the content of the polyetherimide is 50 to 200 parts by mass with respect to 100 parts by mass of the inorganic filler.
- **7.** (**previously presented**): The polyester resin composition of claim 3, wherein the content of the polyetherimide is 50 to 200 parts by mass with respect to 100 parts by mass of the inorganic filler.
- **8. (original):** The polyester resin composition of claim 1, wherein the content of the inorganic filler is 0.5 to 30% by mass with respect to the total mass of the polyester resin composition.
- **9. (original):** The polyester resin composition of claim 2, wherein the content of the inorganic filler is 0.5 to 30% by mass with respect to the total mass of the polyester resin composition.

AMENDMENT UNDER 37 C.F.R. § 1.116 U.S. APPLN. NO. 10/642,577

**10. (original):** The polyester resin composition of claim 3, wherein the content of the inorganic filler is 0.5 to 30% by mass with respect to the total mass of the polyester resin composition.

**11. (original):** The polyester resin composition of claim 5, wherein the content of the inorganic filler is 0.5 to 30% by mass with respect to the total mass of the polyester resin composition.

- 12. (canceled).
- 13. (canceled).
- 14. (canceled).
- 15. (canceled).
- 16. (canceled).
- **17. (original):** The polyester resin composition of claim 1, further comprising a heat-resistance imparting agent.

- **18. (original):** The polyester resin composition of claim 2, further comprising a heat-resistance imparting agent.
- **19. (original):** The polyester resin composition of claim 3, further comprising a heat-resistance imparting agent.
- **20. (original):** The polyester resin composition of claim 5, further comprising a heat-resistance imparting agent.
  - 21. (canceled).